

Solvent Based Coating Vitreset/ Vitreflon Specifications for Mild Steel

Environment	Preparation	Products	Durability - Years to first maintenance				Spec No.
			Atmospheric corrosivity category				
			B Low 2-5	C Medium 5-10	D High 10-15	E High 15-25	
A/C1 Very Low	H/PT Cl 1	V440 V630	●	●	●	●	GPS 1240
B/C2 Low	AB Cl 2.5	V560 V630	●	●			GPS 1241A
		V560 V790	●	●	●	●	GPS 1241B
C/C3 Medium	AB Cl 2.5	V560 V630	●				GPS 1242A
		V560 V790	●	●			GPS 1242B
		V560 V416 V790	●		●		GPS 1242C
		V560 V416 V790	●	●	●	●	GPS 1242D
D/C4 High	AB Cl 2.5	V560 V790	●				GPS 1243A
		V586 V416 V790	●	●			GPS 1243B
		V586 V416 V790	●	●	●		GPS 1243C
		V586 V416 V790	●	●	●	●	GPS 1243D
E/C5 Very high	AB Cl 2.5	V586 V416 V790	●				GPS 1244A
		V586 V416 V790	●	●			GPS 1244B
		V586 V416 V790	●	●	●		GPS 1244C