

Technical Data Sheet No. 536

PVDF Primer

VITRETHANE 183 SLOW

PRODUCT DESCRIPTION: A & I Coatings VITRETHANE 183 SLOW is an olefin based adhesion promoter used for gaining adhesion to PVDF coating.

TYPICAL APPLICATIONS:

Overcoating prefinished aluminium composite panel.

Other PVDF coated substrates.

TECHNICAL INFORMATION:

: Polyolefin. Vehicle Type Pigmentation : Clear.

Dry time : Touch dry 15 - 20mins @25°C. Allow to flash-dry a minimum of 15 mins before

topcoating.

(minimum) Dry to handle 45 mins Full cure 1 hour

Recoat time (minimum)

: 15 minutes at 25°C.

Theoretical Coverage Recommended DFT

: 10m²/Litre/ 5 microns theoretical. : Apply one coat at 60 – 100g/m² wet.

Usual no. of coats

: 1coat.

Flexibility Abrasion Resistance

: Excellent and permanent flexibility. : Excellent after suitably topcoating. : Excellent after suitably topcoating. : Excellent after suitably topcoating. : Excellent after suitably topcoating.

Salt Spray Resistance

Chemical Resistance

Solvent Resistance

Thinning and cleaning: Not normally required. Clean up with V102 Cleaning Thinners.

MERITS:

1. Gives very good adhesion to a wide range of PVDF when used according to specification.

LIMITATIONS:

1. Not tested on every type of PVDF. A trial patch and adhesion test is recommended.

APPLICATION DATA

Mixing : Stir thoroughly before use.

Equipment : Air atomisation or airless.

: Use V102 Cleaning Thinners Cleaning

Typical Specification : Apply 3 microns Vitrethane 183.

Apply Vitreflon 700 topcoat to colour.

QAF034 Version No: 01 Page 1



V183 TDS

SURFACE PREPARATION:

All surfaces to be structurally sound and free of contamination, particularly salt deposits. Oil, grease, dirt etc must be removed with detergent and water blasting or solvent degrease in accordance with AS 1627.1

WORK STOPPAGES: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with **A & I Coatings** recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.

CLEAN UP : Clean all equipment after use with **A & I Coatings** recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including and delays.

PACKING & STORAGE

Packing : Available in 1 or 4L pails. For availability of other sizes, contact A & I Coatings.

Storage : 12 months if stored in sealed containers away from heat and moisture. Subject to re-

inspection thereafter.

HEALTH AND SAFETY: All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for Vitrethane 183. Users should familiarise themselves with all the safety aspects of the product prior to usage.

Please ensure the current Technical Data Sheet is consulted prior to specification or application of **A & I Coatings** products. If the surface intended to be painted differs from the specification, please consult the **A & I Coatings** Technical team on 1800 819 585.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on site conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation.

DISCLAIMER

Since the use and application of this product is beyond our control we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty.

For additional information, phone our Customer Service Centre on 1800 819 585.

October 2015- THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.

QAF034 Version No: 01 Page 2