

VITRETHANE 555



Polyurethane Fast Cure Undercoat

Technical Data Sheet Number 048

PRODUCT DESCRIPTION	<p>A & I Coatings VITRETHANE 555 is a high performance fast cure two pack polyurethane based undercoat/ buildcoat for use on timber, fibreglass, compressed fibrous cement which can then be topcoated with a range of A & I Coatings topcoats.</p>																											
USES & BENEFITS	<p>Can be used as an undercoat/ buildcoat for substrates such as:</p> <ul style="list-style-type: none"> • CFC • Fibreglass • MDF • Melamine 																											
	<p><u>Benefits</u></p> <ol style="list-style-type: none"> 1. Fast drying 2. Positive cure 3. Ease of sanding 4. Good topcoat holdout 	<p><u>Limitations</u></p> <ol style="list-style-type: none"> 1. V555 always should be topcoated, otherwise colour fading may occur 2. For metal coating, a suitable anti-corrosive sealer must be used. V555 may then be used as a sanding sealer 3. Melamine should be sanded to achieve key 																										
PHYSICAL PROPERTIES	<table border="1"> <tr><td>Vehicle Type</td><td>Polyurethane</td></tr> <tr><td>Hardener</td><td>Isocyanate</td></tr> <tr><td>Mixing Ratio</td><td>2 : 1 (Part A : Part B) by Volume</td></tr> <tr><td>Pot Life</td><td>6 hours @ 20°C</td></tr> <tr><td>Finish</td><td>Matt</td></tr> <tr><td>Theoretical Coverage</td><td>5m²/ Litre/ Coat @ 75µmDFT</td></tr> <tr><td>Volume Solids</td><td>38%</td></tr> <tr><td>Recommended DFT</td><td>75µm</td></tr> <tr><td>Usual No. of Coats</td><td>1 – 2 coats</td></tr> <tr><td>Colour</td><td>White, pastels or grey</td></tr> <tr><td>Pigmentation</td><td>Titanium Dioxide</td></tr> <tr><td>Product Weight</td><td>1.39Kg/Litre(Pack A); 0.99Kg/Litre(Pack B)</td></tr> </table>	Vehicle Type	Polyurethane	Hardener	Isocyanate	Mixing Ratio	2 : 1 (Part A : Part B) by Volume	Pot Life	6 hours @ 20°C	Finish	Matt	Theoretical Coverage	5m ² / Litre/ Coat @ 75µmDFT	Volume Solids	38%	Recommended DFT	75µm	Usual No. of Coats	1 – 2 coats	Colour	White, pastels or grey	Pigmentation	Titanium Dioxide	Product Weight	1.39Kg/Litre(Pack A); 0.99Kg/Litre(Pack B)			
Vehicle Type	Polyurethane																											
Hardener	Isocyanate																											
Mixing Ratio	2 : 1 (Part A : Part B) by Volume																											
Pot Life	6 hours @ 20°C																											
Finish	Matt																											
Theoretical Coverage	5m ² / Litre/ Coat @ 75µmDFT																											
Volume Solids	38%																											
Recommended DFT	75µm																											
Usual No. of Coats	1 – 2 coats																											
Colour	White, pastels or grey																											
Pigmentation	Titanium Dioxide																											
Product Weight	1.39Kg/Litre(Pack A); 0.99Kg/Litre(Pack B)																											
ENGINEERING DATA	<table border="1"> <tr><td>Abrasion Resistance</td><td>Fair</td></tr> <tr><td>Flexibility</td><td>Good</td></tr> <tr><td>Bacterial Resistance</td><td>Excellent</td></tr> <tr><td>Chemical Resistance</td><td>Good</td></tr> <tr><td>Dry Heat Resistance</td><td>Good</td></tr> <tr><td>Solvent Resistance</td><td>Excellent</td></tr> <tr><td>Salt Spray Resistance</td><td>Good</td></tr> <tr><td>Durability</td><td>Excellent durability when suitably topcoated</td></tr> </table>	Abrasion Resistance	Fair	Flexibility	Good	Bacterial Resistance	Excellent	Chemical Resistance	Good	Dry Heat Resistance	Good	Solvent Resistance	Excellent	Salt Spray Resistance	Good	Durability	Excellent durability when suitably topcoated											
Abrasion Resistance	Fair																											
Flexibility	Good																											
Bacterial Resistance	Excellent																											
Chemical Resistance	Good																											
Dry Heat Resistance	Good																											
Solvent Resistance	Excellent																											
Salt Spray Resistance	Good																											
Durability	Excellent durability when suitably topcoated																											
CURING DATA	<table border="1"> <tr><td>Substrate Temp.(°C)</td><td>Touch Dry</td><td>Dry to Sand</td><td>Full Cure</td><td>Recoat Min</td></tr> <tr><td>25 °C</td><td>15 Min</td><td>4 Hrs</td><td>7 days</td><td>4 Hrs</td></tr> <tr><td>Note</td><td colspan="4">Dry overnight. Progressively cures over 7 days</td></tr> </table>	Substrate Temp.(°C)	Touch Dry	Dry to Sand	Full Cure	Recoat Min	25 °C	15 Min	4 Hrs	7 days	4 Hrs	Note	Dry overnight. Progressively cures over 7 days															
Substrate Temp.(°C)	Touch Dry	Dry to Sand	Full Cure	Recoat Min																								
25 °C	15 Min	4 Hrs	7 days	4 Hrs																								
Note	Dry overnight. Progressively cures over 7 days																											

APPLICATION DATA	Mixing	Pack A to be mixed thoroughly with Pack B (Hardener) with a hand or mechanical stirring prior to use. The opened containers should be immediately resealed to avoid moist air contamination.
	Application	Air atomisation, airless, electrostatic , HVLP.
	Cleaning	V102 Cleaning Thinners or V111 Medium Thinners.
	Thinning	Thin 5% or as necessary using V108 Medium Thinners (or V112 Retarder when temp above 30° C).
	Typical Specification	<u>MDF Coating:</u> First coat: V555 at 75µm DFT. Sanding with 240/320# sandpaper. Topcoat: Vitrethane 430 to colour @50µmDFT.
SURFACE PREPARATION	All Surfaces	All surfaces to be structurally sound and free of contamination, particularly salt deposits. Loose or flaking paint must be removed by abrasive blast cleaning, power tool cleaning or sanding. Oil, grease, dirt etc must be removed with detergent and water blasting in accordance with AS 1627.1.
	CFC and Cementitious Board	All surfaces to be structurally sound and free of contamination, particularly salt deposits. Loose or flaking paint must be removed by 180 grit sandpaper with orbital sanding to achieve smooth uniform surfaces, providing a sound mechanical key profile for the topcoat to adhere to. Ensure surface is dry and free of all sand, dust, oil, grease and moisture before painting.
	Timber	Thoroughly sand along the grain to remove minor imperfections and any loose surface fibres. Precautions: <ol style="list-style-type: none"> 1. Always coat any end grain thoroughly. 2. Do not coat the timber if moisture content is high. 3. Do the filling of nail holes etc with suitably coloured putty or filler after priming. 4. Give extra attention to corners and edges.
WORK STOPPAGES	General	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with A & I Coatings recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.
	Clean Up	Clean all equipment after use with A & I Coatings recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including and delays.
PACKING & STORAGE	Packing	Available in 6 or 24L packs. For availability of other sizes, contact A & I Coatings.
	Storage	12 months if stored in sealed containers away from heat & moisture. Subject to re-inspection thereafter.
HEALTH & SAFETY	All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for Vitrethane 555. Users should familiarize themselves with all the safety aspects of the product prior to usage. Please ensure the current Technical Data Sheet is consulted prior to specification or application of A & I Coatings products. If the surface intended to be painted differs from the specification, please consult the A & I Coatings Technical team on 1800 819 585.	

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on onsite conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation. **DISCLAIMER** Since the use and application of this product is beyond our control, we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. For additional information, phone our Customer Service Centre on 1800 819 585.

May 2019 - THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.