

ENVIROSET 4113

TECHNICAL DATA SHEET

Two Pack Stipple Finish Solvent Free Epoxy Coating



A & I Coatings ENVIROSET 4113 is a two pack pigmented, stipple finish solvent free 100% solids epoxy with excellent surface hardness and adhesion. It exhibits high water resistance, chemical and oil resistance.

USES & BENEFITS	Uses <ul style="list-style-type: none">• Concrete protection • Floor Coatings • Repaints/ maintenance • Wear resistant • Coating Workshops• Engineering Facilities • Warehouses • Production Plants • Amenities • Carparks etc	
	Benefits <ol style="list-style-type: none">1. Can be used as an intermediate coat and also for a subsequent topcoat for A & I Coatings high performance coating system.2. Exceptionally hard wearing3. Stipple orange peel like finish4. Simple mix ratio5. Easy to clean gloss finish	Limitations <ol style="list-style-type: none">1. Amine bloom may occur if humidity is above 80%.2. Minimum surface temperature should be at least 3 °C above dew point at time of application and initial cure.3. This product will chalk when continuously exposed to sunlight.
	PHYSICAL PROPERTIES	
	Vehicle Type	Epoxy
	Hardener	Amine
	Mixing Ratio	3:1(Part A : Part B) by Volume
	Pot Life	Approx. 25 minutes @25°C. Must be stirred thoroughly.
	Finish	Gloss
	Theoretical Coverage	4-6m ² per litre @160-250µmDFT (160-250µmWFT)
	Volume Solids	100%
	Recommended DFT	160-250µm/coat. Dependent on application
	Usual No. of Coats	2-3 (dependent on substrate)
	Primer Required	Not for concrete. Contact A & I Coatings technical team for specifications.
	Colour	8 standard colours or any RAL or AS 2700S colours.
	Pigmentation	Titanium dioxide and other pigments
	Product Weight	1.41Kg/Litre
ENGINEERING DATA	Abrasion Resistance	Very good
	Chemical Resistance	Enviroset 4113 displays resistance to many common chemicals in spill or splash situations at ambient temperatures. The following chemicals are an example only. Consult A&I for specific applications. <ul style="list-style-type: none">• Hydrochloric Acid (10%)• Nitric Acid (10%)• Sulfuric acid (40%)• Uric acid (concentrated)• Sodium hydroxide (10%)• Hydrogen peroxide (3%)• Motor Oil• Toluene• Brake Fluid• Skydrol• Organic Food Matter• Grease• Wine• Diesel• Hydrocarbon solvents Some chemicals may cause surface staining from prolonged exposure without impacting the coating integrity. Data is available on request. Exposure based on spill and splash cleaned within 24hrs.
	Dry Heat Resistance	Up to 120°C
	Hot water resistance	Up to 70°C
	Durability	Excellent, but will chalk under UV exposure without damage to the integrity of the coating.
	Solvent Resistance	Excellent for many solvents

ENVIROSET 4113

TECHNICAL DATA SHEET

Two Pack Stipple Finish Solvent Free Epoxy Coating



CURING DATA	Substrate Temp.(°C)	Foot Traffic	Vehicular Traffic	Full Cure	Recoat Time min
	25 °C	24 Hrs	72 Hrs	7 Days	12 Hrs
Note: When overcoating with an epoxy based topcoat, this should occur within 36hrs at 25°C. No water or condensation should contact the coating for 5 days from installation.					
SURFACE PREPARATION	Concrete	Allow new concrete to cure for minimum 28 days prior to coating. Surface must be sound, dry, free from all loose material, laitance, old coatings, dust and surface contaminants (e.g. oil, grease, chemicals, release/curing agents etc). Substrates must be mechanically treated by abrasive blasting or grinding to achieve a clean anchor pattern for best adhesion. Oily surfaces must be detergent cleaned and water blasted. Please note that moisture content in the concrete must be no greater than 4% pbw prior to application of the E4113. Ensure no rising moisture will occur in concrete by means of an effective subgrade damp proof membrane. Concrete to be min 25Mpa compressive strength and 1.5Mpa pull off strength.			
	Mixing	Power stir Pack A, then blend with Pack B to correct ratio. Power stir thoroughly for two minutes prior to use. Only mix required amount and use within the stated pot life. If Using Unpigmented Pack A, add the 1kg Colour pot to Pack A and mix for 1 minute before adding Pack B and mixing again for 2 minutes.			
APPLICATION DATA	Application	10-13mm Nap Roller.			
	Ambient Temperature	Apply between 8-35°C			
	Thinning	If required, use Methylated Spirits or V122 Epoxy Thinners. Maximum thinner addition is 10% of mixed quantity and only added after Pack A and B has been mixed. After Thinners added, a further 45 seconds mixing is required.			
	Cleaning	Use Xylene or Acetone for clean-up.			
PACKING & STORAGE	Packing	Available in 10L packs. For other sizes, contact A & I Coatings.			
	Storage	12 months if stored in sealed containers away from heat and moisture. Subject to re-inspection thereafter.			

All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for ENVIROSET 4113. Users should familiarise themselves with all the safety aspects of the product prior to use. Please ensure the current Technical Data Sheet is consulted prior to specification or application of A & I Coatings products. A & I Coatings will in many instances provide Area Specific Instruction Sheets which contain detailed instructions on how to achieve desired results for specific areas. If the surface intended to be painted differs from the specification, please consult the A & I Coatings Technical team on 1800 819 585.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on onsite conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation. **DISCLAIMER** Since the use and application of this product is beyond our control, we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. For additional information, phone our Customer Service Centre on 1800 819 585, or e-mail helpdesk@aicoatings.com Visit our website for more products: www.aicoatings.com



PO Box 820
Moss Vale NSW 2577

7 Lackey Road
Moss Vale NSW 2577

Australia **1800 819 585**
International **+61 2 4869 1441**
Fax **+61 2 4869 3031**
Email helpdesk@aicoatings.com
www.aicoatings.com