

# ENVIROSET 2100

## TECHNICAL DATA SHEET

Two Pack Water Based Epoxy. Vapour permeable.



A & I Coatings ENVIROSET 2100 is a two-pack water borne epoxy coating with excellent film properties and surface hardness. It is a self-priming and environmentally friendly coating system which is ideal as a floor coating, due to its excellent adhesion and chemical resistance. It can be tinted to an unlimited colour range.

<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>• Factories and warehouses • Food and beverage industry • Hospitals, shopping centres, schools and laboratories • Chemical industry • Retaining walls • Seamless flooring</li> </ul>				
	<b>Benefits</b> <ol style="list-style-type: none"> <li>1. Can be easily brushed or rolled.</li> <li>2. Excellent surface hardness and water resistance</li> <li>3. May be applied down to 8°C.</li> <li>4. Vapour permeable breathable coating.</li> </ol>	<b>Limitations</b> <ol style="list-style-type: none"> <li>1. Amine bloom may occur if humidity is above 80%. Use ventilation lower humidity if above 80% or likely to be above 80% over curing period.</li> <li>2. Minimum surface temperature should be at least 3°C above dew point.</li> <li>3. Chalking will occur during full sunlight exposure without loss of film integrity. Can be over coated with Envirothane/Vitrethane topcoats for UV resistance.</li> </ol>			
<b>PHYSICAL PROPERTIES</b>	Vehicle Type	Epoxy			
	Hardener	Polyamide			
	Ratio	1:1 (Pack A : Pack B) by Volume			
	Pot Life	1 hour@25°C			
	Finish	Semigloss			
	Theoretical Coverage	6 - 10m <sup>2</sup> /litre @ 40 to 60µm DFT (100 - 170 µm WFT) per coat			
	Volume Solids	38% by Volume			
	Recommended DFT	Typically, 40 - 60µm DFT per coat dependent on application			
	Usual No. of Coats	2 – 3 coats			
	Colour	Light Grey AS 2700 N35 or other colours on request			
	Pigmentation	Titanium dioxide or other			
	Primer Required	Not on concrete. Contact A & I Coatings for use on other substrates			
	Product Weight	Approx. 1.12Kg/Litre dependant on colour			
VOC Content	<27 grams/Litre				
<b>ENGINEERING DATA</b>	Abrasion Resistance	Very good. NB. Black, dark, and strong colours will benefit with the addition of a thin coat of E2000 Clear or E8470 Clear to maximize mar resistance			
	Chemical Resistance	Enviroset 2100 displays resistance to many common chemicals in spill or splash situations at ambient temperatures. The following chemicals are an example only. Consult A&I for specific applications. <table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td> <ul style="list-style-type: none"> <li>• Hydrochloric Acid (10%)</li> <li>• Nitric Acid (10%)</li> <li>• Sulfuric acid (40%)</li> <li>• Uric acid (concentrated)</li> <li>• Sodium hydroxide (10%)</li> </ul> </td> <td> <ul style="list-style-type: none"> <li>• MEK</li> <li>• Kerosene</li> <li>• Turpentine</li> <li>• Skydrol</li> <li>• Hydraulic Fluid</li> </ul> </td> <td> <ul style="list-style-type: none"> <li>• Organic Food Matter</li> <li>• Grease</li> <li>• Wine</li> <li>• Diesel</li> </ul> </td> </tr> </table>		<ul style="list-style-type: none"> <li>• Hydrochloric Acid (10%)</li> <li>• Nitric Acid (10%)</li> <li>• Sulfuric acid (40%)</li> <li>• Uric acid (concentrated)</li> <li>• Sodium hydroxide (10%)</li> </ul>	<ul style="list-style-type: none"> <li>• MEK</li> <li>• Kerosene</li> <li>• Turpentine</li> <li>• Skydrol</li> <li>• Hydraulic Fluid</li> </ul>
<ul style="list-style-type: none"> <li>• Hydrochloric Acid (10%)</li> <li>• Nitric Acid (10%)</li> <li>• Sulfuric acid (40%)</li> <li>• Uric acid (concentrated)</li> <li>• Sodium hydroxide (10%)</li> </ul>	<ul style="list-style-type: none"> <li>• MEK</li> <li>• Kerosene</li> <li>• Turpentine</li> <li>• Skydrol</li> <li>• Hydraulic Fluid</li> </ul>	<ul style="list-style-type: none"> <li>• Organic Food Matter</li> <li>• Grease</li> <li>• Wine</li> <li>• Diesel</li> </ul>			

# ENVIROSET 2100

## TECHNICAL DATA SHEET

Two Pack Water Based Epoxy. Vapour permeable.



ENVIRO  
*choice*

<b>ENGINEERING DATA</b>	Chemical Resistance	<ul style="list-style-type: none"> <li>Hydrogen peroxide (3%)</li> <li>Hydrocarbon solvents</li> </ul>	<ul style="list-style-type: none"> <li>Toluene</li> </ul>	<ul style="list-style-type: none"> <li>Brake Fluid</li> <li>Motor Oil</li> </ul>	
		Some chemicals may cause surface staining from prolonged exposure without impacting the coating integrity. Data is available on request. Exposure based on spills and splashes cleaned within 24hrs.			
	Salt Spray Resistance	Very Good			
	Dry Heat Resistance	120 °C			
	Solvent Resistance	Good			
	Hot water resistance	70 °C			
Durability	Excellent for indoor application, topcoat needed for exterior				
<b>CURING DATA</b>	Substrate Temp.(°C)	Foot Traffic	Vehicle Traffic	Full Cure	Recoat Min
	Standard Hardener 25°C	24 Hrs	4 Days	7 Days	4 hrs (based on good airflow)
	Note: When overcoating E2100 with itself, application to occur within 48hrs at 25°C. No water or condensation should contact the coating for 5 days from installation.				
<b>SURFACE PREPARATION</b>	General	All surfaces to be structurally sound and free of contamination, particularly salt deposits. Loose or flaking paint must be removed by abrasive blast cleaning, power tool cleaning or sanding. Oil, grease, dirt etc must be removed with detergent and water blasting in accordance with AS 1627.1.			
	Concrete	Allow new concrete surfaces to cure to be <6% moisture PBW. Surface to be coated should be free from oil, grease. To get uniform surface profile, use shot blasting or diamond grinding. Concrete to be min 25Mpa compressive strength and 1.5Mpa pull off strength.			
	Aluminium, galvanised steel & Zinalume	Remove oil and degrease with mild detergent or with solvent to AS 1627.1. Slightly roughen the surface by sanding or light whip blasting with a non-metallic abrasive. Apply suitable primer according to specification			
	Existing painted surfaces	All surfaces should be free from oil, grease and other contaminates, and loose and unsound paint. The existing coating must be thoroughly abraded and adhesion of E2100 to the existing coating checked prior to commencing the project.			
<b>APPLICATION DATA</b>	Mixing	Power stir Pack A then blend Pack A with Pack B and power stir thoroughly for at least 2 minutes before thinning. Thin 1st coat up to 20% with clean water and final coat up to 5% with clean water.			
	Ambient Temperature	Apply between 8-35°C			
	Application	Airless spray (rec tip range = 15 – 19Thou), roller or brush.			
	Cleaning	Use Water or Acetone			
Thinning	Water. N.B. Always stir Part A & B together well, before adding water. After water mix again for 60 seconds.				

# ENVIROSET 2100

## TECHNICAL DATA SHEET

Two Pack Water Based Epoxy. Vapour permeable.



<b>WORK STOPPAGES</b>	General	Do not allow material to remain in hoses, gun or spray equipment. Once units of paint have been mixed, they should not be resealed, and it is advised that after prolonged stoppages work commences with freshly mixed units.
	Clean Up	Clean all equipment after use with A & I Coatings recommended cleaner. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time (including delays).
<b>PACKING &amp; STORAGE</b>	Packing	Available in 4L or 20L Packs. For availability of other sizes, contact A&I Coatings.
	Storage	12 months if stored in sealed containers away from heat and moisture. Subject to re-inspection thereafter.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on-site conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation.

DISCLAIMER: Since the use and application of this product is beyond our control we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty