

ENDURAFLOOR RC UV

SYSTEM DATA SHEET

Heavy duty epoxy & polyurethane roller applied system with excellent UV resistance



Technical Snapshot

Shore D

80

Bond Strength to Concrete

> 1.5 MPa

Abrasion Resistance ASTM D4060

60mg / 500 cycles, CS17, 1kg

Fire Resistance AS ISO 9239.1:2013

CRF 8 kW/m²

Smoke development rate 400%/minute

Chemical Resistance

Good

- | | |
|-----------------------|----------------------|
| ■ Brake Fluid | ■ Motor Oil |
| ■ 5% Acetic Acid | ■ Diesel |
| ■ 40% Sulphuric Acid | ■ Hydraulic Fluid |
| ■ Hydrocarbon Solvent | ■ Jet Fuel / Skydrol |

The chemicals listed above are examples only and are based on ambient temperature, non-immersion exposure conditions.

Contact A&I Coatings for further information, including advice on chemicals not listed.

Aesthetic staining may occur and is not considered a product failure.

Spills and splashes should be cleaned and removed within 24 hours.

Feature & Benefits

- Variable slip-resistant profiles from P1–P5 in accordance with AS 4586:2013
- Economical and well suited for large areas
- Light reflective
- Satin or Gloss Finish
- Easy to clean
- Suitable for pedestrian, vehicle and forklift traffic
- Good chemical resistance
- UV stable and suitable for external use
- Wide colour range
- Seamless finish



Typical Uses

- Aircraft Hangers
- Data Centres
- Garages
- Walkways
- Warehouses
- Area subject to full UV exposures
- Educational Facilities
- Engineering Facilities
- Storage Facilities
- Stadiums
- Workshops

ENDURAFLOOR RC UV

SYSTEM DATA SHEET

Heavy duty epoxy & polyurethane roller applied system with excellent UV resistance



Preparation and Substrate Requirement

- Suitable substrates include concrete, compressed fibre cement and mineral-based substrates
- Substrate must have a minimum compressive strength of 25 MPa and tensile bond strength of 1.5 MPa.
- Substrate must be free from rising moisture and have an effective damp proof membrane beneath.
- Substrate moisture content must be below 4.5% by weight when tested in accordance with ASTM F2659
- Surface must be sound, dry and free from loose material, laitance, old coatings, dust and surface contaminants, including oil, grease, chemicals, release agents and curing compounds.
- Concrete must be suitably prepared to ensure good coating adhesion. This can be achieved by diamond grinding or shot blasting to a minimum ICRI CSP 2 surface profile.
- Remove all loose material by industrial vacuum cleaning.

Application Conditions

- Substrate surface temperature must be at least 3°C above the dew point during application and initial cure.
- Ambient and substrate temperatures should be between 10°C and 35°C during application and curing.
- Relative humidity must be below 85% during application and initial cure.

Curing Time

- Pedestrian Traffic: 24 Hours at 20°C
- Vehicle Traffic: 72 Hours at 20°C
- Full cure: 7 days at 20°C
- Ensure no water contact for at least 2 days at 20°C
- Curing times are subject to change depending on ambient temperature

For Specifier

Specify:

"Floor System to be Endurafloor RC UV as manufactured by A&I Coatings P/L."

Options	Thickness	Slip Rating	Colour	Finish
	Roll coats	P1 – P5	Choose from standard colour or any AS 2700 colour	Gloss / Satin

Standard Colours:



ENDURAFLOOR RC UV

SYSTEM DATA SHEET

Heavy duty epoxy & polyurethane roller applied system with excellent UV resistance



System Build Up

Refer to individual Technical Data Sheet for detailed product information

- Apply Enviroset 4110, Enviroset 4113 or Enviroset 4116 at 5 – 7 m²/L by roller.
- Apply Enviroset 4110, Enviroset 4113 or Enviroset 4116 at 5 – 7 m²/L by roller. Incorporate appropriate aggregate if slip resistance of P2 – P5 is required. Contact A&I Coatings for further information.
- Apply Vitrethane 633 at 7 – 8 m²/L by roller.
- Recoat windows must be followed according to the relevant product TDS.
- If the recoat window is exceeded, mechanically abrade the surface before recoating.



Important Note

- If there is any doubt regarding substrate suitability, conduct a site test before application.
- Do not apply over substrates with rising damp or hydrostatic pressure.
- Expansion joints must be reflected through the system and filled with a flexible joint sealer after system application.
- Dynamic crack movement may transfer through the floor system and may result in a visible cracking at the surface.
- For consistent colour, ensure the colour is from the same batch throughout the project.
- Coverage rates are approximate and may vary depending on substrate condition, surface profile, application method and site conditions. Conduct site tests to verify actual coverage.
- Do not expose the system to chemicals, heavy traffic or wash-down until full cure has been achieved.
- Users must read the Safety Data Sheet for each product used in the system and familiarise themselves with all safety, handling and personal protective equipment requirements before use.