

# VITREZONE 425

## TECHNICAL DATA SHEET

Two Pack High Build Epoxy Barrier Coating



A & I Coatings **VITREZONE 425** is a high solids polyamine cured epoxy coating formulated to achieve high film builds in a single coat. VITREZONE 425 will continue to cure underwater and is well suited to the maintenance of structures subject to tidal movements. VITREZONE 425 is a Surface Tolerant Epoxy and may be applied to damp surfaces and steel which has gingered after blasting.

<b>USES &amp; BENEFITS</b>	Oil rigs/refineries • Chemical plants • Galvanised steel • Hydro-electric installations • Waste/water treatment plants • Pulp and paper mills • Structural steel • Tank farms • Aluminium • Stainless steel			
	Benefits-			
	1. Excellent barrier to water and oxygen.	3. Continues to cure after immersion in water.		
	2. Can be used for immersion in water or sewerage.	4. Adequate flexibility for normal substrate movement		
<b>PHYSICAL PROPERTIES</b>	Vehicle Type	Two component epoxy		
	Hardener	Polyamine		
	Mixing Ratio	4: 1 (Part A : Part B) by Volume		
	Pot Life	1.5 hours@25°C		
	Finish	Satin		
	Theoretical Coverage	2.4m <sup>2</sup> /L @ 350µm/coat. (DFT)		
	Volume Solids	85 ± 2 %		
	Recommended DFT	350µm DFT minimum, may be applied at up to 500 microns dry film thickness in a single coat.		
	Usual No. of Coats	1 to 2		
	Colour	Unlimited colour range available		
	Pigmentation	Colours, MIOX, Glass Flake and Aluminium Flake		
Product Weight	1.5 – 1.8 Kg/Litre (after mixing)			
<b>ENGINEERING DATA</b>	Abrasion Resistance	Excellent		
	Flexibility	Good		
	Chemical Resistance	Acid – Good. Alkali – Good. Contact A & I Coatings for specific recommendations		
	Solvent Resistance	Excellent		
	Dry Heat Resistance	Up to 120°C		
	Durability	Excellent, will discolour on exterior exposure however this in no way affects product function or performance.		
<b>CURING DATA</b>	Substrate Temp.(°C)	Surface Dry	Full Cure	Recoat Min
	10°C	12 Hrs	7 Days	18 Hrs
	25°C	4 Hrs	5 Days	6 Hrs
	40°C	1.5 Hrs	3 Days	2 Hrs

# VITREZONE 425

## TECHNICAL DATA SHEET

Two Pack High Build Epoxy Barrier Coating



<b>APPLICATION DATA</b>	Mixing	Power stir Pack A, then blend with Pack B and power stir thoroughly for a minimum of three minutes. Only mix complete kits and use within the stated pot life. In temperatures under 10°C allow a 5-minute induction time after mixing Part A and B together.
	Application	Apply by airless spray using a tip size of 21-26 thou. Brush and roller is not recommended but for small touch up work use a 10 – 13mm nap roller or brush, taking care to apply at specified coverage rate. If application is done by roller, multiple coats may be required to achieve the specified film build.
	Cleaning	V122 Epoxy Thinners.
	Thinning	If necessary, thin with V122 Epoxy Thinners. Not normally required.
<b>SURFACE PREPARATION</b>	All Surfaces	All surfaces to be structurally sound and free of contamination, particularly salt deposits. Loose or flaking paint must be removed by abrasive blast cleaning, power tool cleaning or sanding, to AS 1627. Oil, grease, dirt etc must be removed with detergent and water blasting or solvent cleaning to AS1627.1. Primers should be abraded as necessary.
	Repaints	All surfaces should be free from oil, grease, loose paint and other contaminants. For unusual substrates, a test patch is recommended before use.
	Steel	Degrease the surfaces and remove all weld spatter and flux. Grind sharp edges and corners. For best results abrasive blast clean to Sa2½. Please consult A & I Coatings Technical team for particular specifications.
<b>WORK STOPPAGES</b>	General	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with A & I Coatings recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.
	Clean Up	Clean all equipment after use with A & I Coatings recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, (including delays).
<b>PACKING &amp; STORAGE</b>	Packing	Available in 20L kits. For availability of other sizes, contact A & I Coatings.
	Storage	24 months if stored in sealed containers away from heat and moisture. Subject to re-inspection thereafter.
<b>HEALTH &amp; SAFETY</b>	All applicable statutory regulations must be observed in the application of this product. Users must first read the Safety Data Sheet for V425. Users should familiarize themselves with all the safety aspects of the product prior to usage	

# VITREZONE 425

## TECHNICAL DATA SHEET

Two Pack High Build Epoxy Barrier Coating



All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on onsite conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation. **DISCLAIMER** Since the use and application of this product is beyond our control, we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. For additional information, phone our Customer Service Centre.



PO Box 820 Moss Vale, NSW 2577

7 Lackey Road Moss Vale NSW 2577

Australia 1800 819 585

International +61 2 4869 1441

Fax +61 2 4868 3031

Email [helpdesk@aicoatings.com](mailto:helpdesk@aicoatings.com)

[www.aicoatings.com.au](http://www.aicoatings.com.au)